

## ABS FibraQ compound (15% wood fibers)

### Description:

Compounded formulation containing ABS with 15% FibraQ mixed via a Twinscrew extruder. The granulate also include 2% coupling agent.



FibraQ is Biofiber Tech's product, consisting of surface-modified wood fibers with enhanced hydrophobicity, low moisture absorption and high flowability within polymer matrices.

### General

Processing Method	Injection molding
Forms	Pellets
Filler	Surface modified wood fiber, 15% filler by weight
Density	Ca. 1.08 g/cm <sup>3</sup>
Renewable carbon content	15%
Recommended Processing temperature	190-210°C
Code name	ABS02-15

### Typical properties:

Feature	Method	Unit	Values
Tensile strength at Break	ISO 527-2:2012	MPa	57.1
Tensile modulus	ISO 527-2:2012	MPa	3366
Elongation at Break	ISO 527-2:2012	%	2.7
MFI (190°C, 5kg)	ISO 1133-1:2012	(g/10 min)	1.94

*The values were measured on standardized test specimens and can be affected by pigmentation, mould design and processing conditions. Biofiber Tech is therefore not responsible for the accuracy of the provided values and cannot give any warranty with regard to the correctness.*

*Any information, whether verbally or written, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigation. The buyer is solely responsible for confirming the suitability of the product for their specific application.*